

Medium	Ecoguss	
1,1,1-trichloroethane	RT	✓
Acetic acid	99 %	✓
Acetone	RT	✓
Formic acid	85 %	✓
Ammoniac 24.5 %	RT	✓
Petrol/benzene mixture	RT	✓
Brake fluid	RT	✓
Butyl alcohol, n-butanol	RT	✓
Calcium chloride	RT	✓
Calcium base liquor	RT	✓
25 % chlorine solution	RT	✓
Diesel	RT	✓
Diethyl ether	RT	✓
Acetic acid 99 %	RT	✓
Ethanol	RT	✓
Ethylene glycol	RT	✓
FAM-DIN 51604-A	RT	✓
FAM-DIN 51604-B	RT	✓
FAM-DIN 51604-C	RT	✓
Frigene 114 (tetrafluorodichloroethane)	RT	✓
Frigene R134 + 5 % Aral Alur EE 32	RT	✓
Hydraulic fluid	RT	✓
Isopropanol	RT	✓
Potassium chromate 30 %	RT	✓
Potassium base liquor 45 %	RT	✓
Potassium permanganate 6 % (80°)	RT	✓

Medium	Ecoguss	
Kerosine	RT	✓
Methanol	RT	✓
Methyl-tert.-butylether	RT	✓
Lactic acid	90 %	✓
Motor oil	150°	✓
Sodium chloride, saturated	RT	✓
Sodium hypochlorite (80°)	RT	✓
Sodium base liquor 30 %	RT	✓
Sodium base liquor 50 %	RT	✓
n-butyl acetate	RT	✓
n-hexane	RT	✓
Phosphoric acid 40 %	RT	✓
Rapeseed methyl ester	RT	✓
Reference petrol C, ASTM D-471	RT	✓
Nitric acid 10 %	RT	✓
Nitric acid 65 %	RT	✓
Hydrochloric acid	37 %	✓
Sulphuric acid	37 %	✓
Silicone oil	RT	✓
Toluol	RT	✓
Water 90°C up to 1000 h	RT	✓
Water, cold	RT	✓
Xylene	RT	✓
Zinc chloride solution (50 wt.%)	RT	✓
Zinc chloride solution 10 %	RT	✓
Citric acid	RT	✓

Medium	PP	
Acetone	100 %	23° ✓
Formic acid	98 %	23° ✓
Ammonium sulphate		to 100° ✓
Amyl alcohol		60° ✓
Petrol/benzene mixture		23° ✓
Brake fluid		to 60° ✓
Bromine		-
Butane		to 60° ✓
Calcium hypochlorite	12.5 % active Cl	to 60° ✓
Chlorine, liquid		-
Citric acid	saturated	to 100° ✓
Acetic acid	100 %	23° ✓
Hydrofluoric acid	40 %	to 60° ✓
Formaldehyde		to 60° ✓
Glycerine	100 %	to 60° ✓
Magnesium chloride	saturated	to 100° ✓
Methanol	100 %	to 60° ✓
Lactic acid	10 %	to 60° ✓
Motor oil		23° ✓
Sodium chloride	saturated	to 100° ✓
Sodium thiosulphate	saturated	to 60° ✓
Nitrobenzene	100 %	60° ✓
Perchloroethylene		23° ✓
Phenol	saturated	to 60° ✓
Propanol	100 %	to 60° ✓
Nitric acid	50 %	23° ✓
Hydrochloric acid		to 60° ✓
Sulphuric acid	to 10 %	to 100° ✓
Detergent	ready to use	to 60° ✓
Nitrogen peroxide	3 %	to 100° ✓

ABS	
	-
40 %	to 50° ✓
saturated	to 100° ✓
	23° ✓
	-
	-
	23° ✓
saturated	to 50° ✓
	-
saturated	to 50° ✓
to 50 %	to 50° ✓
40 %	23° ✓
30 %	50° ✓
	to 50° ✓
saturated	to 50° ✓
	to 20° ✓
10 %	to 50° ✓
	to 50° ✓
saturated	to 50° ✓
saturated	to 50° ✓
	-
	-
10 %	50° ✓
	to 50° ✓
30 %	23° ✓
37 %	23° ✓
to 50 %	50° ✓
ready to use	23° ✓
3 %	to 50° ✓

✓ > εξαιρετικά ανθεκτικό

✓ > μέτρια ανθεκτικό

— > ακατάλληλο για χρήση

RT > θερμοκρασία δωματίου